

Range: Specialty

Colour: Pacific

SKU: 250160013320000617150

Technical Data

Length (mm)	230	Initial Rate of Absorption (IRA) (kg/m ² min)	0.1-4.0
Width (mm)	110	Coefficient of Expansion e'Factor (mm/m)	<1.2
Height (mm)	76	Liability to Efflorescence	Nil to slight
Dimensional Category	DW1	Lime Pitting Liability	Nil to slight
Average Weight / Unit (kg)	2.8	Solar Absorption	0.78
Core Volume (%)	30-40	Basix	Dark
Units per Square Metre	48.5	Place of Manufacture	New South Wales
Pack Size	512	Product Warranty	100 Years
Characteristic Unconfined Compressive Strength (f 'uc) MPa	>20	Solar Absorption	0.78
Maximum Cold Water Absorption (%)	<10		

A BRAND OF

BRICKWORKS