

La Paloma Rustico Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f'uc) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m2 min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
La Paloma Rustico	Gaudi			CQLD	480	100	40	DW1	4.9	35	240	15	8	1.0	1.2	Exposure Grade	Slight	Slight	
La Paloma Rustico	Miro			CQLD	480	100	40	DW1	4.9	35	240	15	8	1.0	1.2	General Purpose	Slight	Slight	71.7

This Data represents average results from commercial production lots.
If specific test results are required, sample should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

