

San Selmo Smoked Range Technical Data Sheet

BRICKWORKS

| Product Range | Product Name | Dimension Illustration | Swatch | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Core Volume (%) | Units per Square Metre | Pack Size | Characteristic Unconfined Compressive Strength (f _{uc}) MPa | Maximum Cold Water Absorption (%) | Initial Rate of Absorption (IRA) (kg/m ² min) | Coefficient of Expansion Factor (mm/m) | Durability Class | Liability to Efflorescence | Lime Pitting Liability | LRV |
|------------------|---------------|---|---|-------|-------------|------------|-------------|----------------------|-----------------|------------------------|-----------|---|-----------------------------------|--|--|------------------|----------------------------|------------------------|------|
| San Selmo Smoked | Grey Cashmere |  |  | CQLD | 230 | 110 | 76 | DW0 | Solid | 48.5 | 216 | >10 | <15 | <3.0 | <1.0 | General Purpose | Slight | Slight | 46.3 |
| San Selmo Smoked | Opaque Slate |  |  | CQLD | 230 | 110 | 76 | DW0 | Solid | 48.5 | 216 | >10 | <15 | <3.0 | <1.0 | General Purpose | Slight | Slight | 25.3 |
| San Selmo Smoked | Cloudy Silver |  |  | CQLD | 230 | 110 | 76 | DW0 | Solid | 48.5 | 216 | >10 | <15 | <3.0 | <1.0 | General Purpose | Slight | Slight | 22.8 |

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.