

Specialty Range Technical Data Sheet

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion e'Factor (mm/m)	Liability to Efflorescence	Lime Pitting Liability
Specialty	Espresso			NQLD	230	110	76	DW1	2.8	48.5	512	>20	10	0.1-4.0	1.2	Nil to slight	Nil to slight
Specialty	Sienna			NQLD	230	110	76	DW1	2.8	48.5	512	>20	10	0.1-4.0	1.2	Nil to slight	Nil to slight
Specialty	Royal			NQLD	230	110	76	DW1	2.8	48.5	512	>20	10	0.1-4.0	1.2	Nil to slight	Nil to slight
Specialty	Crimson			NQLD	230	110	76	DW1	2.8	48.5	512	>20	10	0.1-4.0	1.2	Nil to slight	Nil to slight
Specialty	Pacific			NQLD	230	110	76	DW1	2.8	48.5	512	>20	10	0.1-4.0	1.2	Nil to slight	Nil to slight
Specialty	Emerald			NQLD	230	110	76	DW1	2.8	48.5	512	>20	10	0.1-4.0	1.2	Nil to slight	Nil to slight
Specialty	Jade			NQLD	230	110	76	DW1	2.8	48.5	512	>20	10	0.1-4.0	1.2	Nil to slight	Nil to slight
Specialty	Amber			NQLD	230	110	76	DW1		48.5	512	>20	10	0.1-4.0	1.2	Nil to slight	Nil to slight

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.