











# Urban One Range Technical Data Sheet

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f <sub>uc</sub> ) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Urban One	Chiffon			NQLD	230	110	76	DW1	48.5	400	>10	10	0.5-1.5	1.2	General Purpose	Slight	Slight	
Urban One	Grecian Gold			NQLD	230	110	76								Exposure Grade			15.6
Urban One	Pepper			NQLD	230	110	76	DW1	48.5	400	>15	10	0.1-1.0	1.0	Exposure Grade	Slight	Slight	13.7
Urban One	Sea Salt			NQLD	230	110	76								Exposure Grade			35
Urban One	Silver			NQLD	230	110	76	DW1	48.5	400	>15	10	0.1-1.0	1.0	Exposure Grade	Slight	Slight	30.3

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.