




Alfresco Range Technical Data Sheet

BRICKWORKS

| Product Range | Product Name | Swatch | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Average Weight / Unit (kg) | Units per Square Metre | Pack Size | Maximum Cold Water Absorption (%) | Coefficient of Expansion e Factor (mm/m) | Durability Class | Liability to Efflorescence | Lime Pitting Liability | LRV |
|---------------|--------------|---|-------|-------------|------------|-------------|----------------------|----------------------------|------------------------|-----------|-----------------------------------|--|------------------|----------------------------|------------------------|-----|
| Alfresco | Buttermilk |  | NQLD | 230 | 115 | 50 | DPA2 | 2.8 | 37 | 480 | 10 | 1 | Exposure Grade | Slight | Slight | 25 |
| Alfresco | Hickory |  | NQLD | 230 | 115 | 50 | DPA2 | 2.8 | 37 | 480 | 10 | 1 | Exposure Grade | Slight | Slight | 8.2 |
| Alfresco | Roux |  | NQLD | 230 | 115 | 50 | DPA2 | 2.8 | 37 | 480 | 10 | 1 | Exposure Grade | Slight | Slight | 9.6 |

This Data represents average results from commercial production lots.
If specific test results are required, sample should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.