

























San Selmo Corso Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Core Volume (%)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
San Selmo Corso	Piave Standard			NQLD	500	100	40	DW0	Solid	40.8		>10	<25	1.0-8.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	
San Selmo Corso	Potenza Handmade			NQLD	500	100	40	DW0	Solid	40.8	137	>10	<25	1.0-8.0	<1.2	General Purpose	Nil to slight	Nil to slight	9.2
San Selmo Corso	Marana Standard			NQLD	500	100	40	DW0	Solid	40.8		>10	<25	1.0-8.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	14.8
San Selmo Corso	Potenza Standard			NQLD	500	100	40	DW0	Solid	40.8		>10	<25	1.0-8.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	9.2
San Selmo Corso	Marana Handmade			NQLD	500	100	40	DW0	Solid	40.8	137	>10	<25	1.0-8.0	<1.2	General Purpose	Nil to slight	Nil to slight	14.8
San Selmo Corso	Livenza Standard			NQLD	500	100	40	DW0	Solid	40.8		>10	<25	1.0-8.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	20.1
San Selmo Corso	Brenta Handmade			NQLD	500	100	40	DW0	Solid	40.8	137	>10	<25	1.0-8.0	<1.2	General Purpose	Nil to slight	Nil to slight	48.5
San Selmo Corso	Arno Standard			NQLD	500	100	40	DW0	Solid	40.8		>10	<25	1.0-8.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	19
San Selmo Corso	Livenza Handmade			NQLD	500	100	40	DW0	Solid	40.8	137	>10	<25	1.0-8.0	<1.2	General Purpose	Nil to slight	Nil to slight	20.1
San Selmo Corso	Brenta Standard			NQLD	500	100	40	DW0	Solid	40.8		>10	<25	1.0-8.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	48.5
San Selmo Corso	Piave Handmade			NQLD	500	100	40	DW0	Solid	40.8	137	>10	<25	1.0-8.0	<1.2	General Purpose	Nil to slight	Nil to slight	
San Selmo Corso	Arno Handmade			NQLD	500	100	40	DW0	Solid	40.8	137	>10	<25	1.0-8.0	<1.2	General Purpose	Nil to slight	Nil to slight	19

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.