

Thin Brick Range Technical Data Sheet






| Product Range | Product Name | Dimension Illustration | Swatch | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Units per Square Metre | Pack Size | Maximum Cold Water Absorption (%) | Initial Rate of Absorption (IRA) (kg/m ² min) | Coefficient of Expansion e Factor (mm/m) | Durability Class | Liability to Efflorescence | Lime Pitting Liability | LRV |
|---------------|--------------------------|------------------------|--------|-------|-------------|------------|-------------|----------------------|------------------------|-----------|-----------------------------------|--|--|------------------|----------------------------|------------------------|------|
| Thin Brick | Limewash Corner Unit | | | NQLD | 230 | 110 | 76 | DW0 | | 1008 | <17 | 4.0-8.0 | | General Purpose | Slight | Slight | |
| Thin Brick | Original Facing Unit | | | NQLD | 230 | 22 | 76 | DW0 | 48.5 | 2160 | <17 | 4.0-8.0 | | General Purpose | Slight | Slight | |
| Thin Brick | Castellana Corner Unit | | | NQLD | 230 | 110 | 76 | DW1 | | 1200 | <6 | <0.8 | | Exposure Grade | Slight | | 67 |
| Thin Brick | Limewash Facing Unit | | | NQLD | 230 | 22 | 76 | DW0 | 48.5 | 2160 | <17 | 4.0-8.0 | | General Purpose | Slight | Slight | |
| Thin Brick | Azul Facing Unit | | | NQLD | 230 | 22 | 76 | DW1 | 48.5 | 1920 | <6 | <0.8 | | Exposure Grade | Slight | | 13.1 |
| Thin Brick | Glazed White Corner Unit | | | NQLD | 230 | 110 | 76 | DW1 | | 1200 | <6 | <0.8 | | Exposure Grade | Slight | | 66.4 |
| Thin Brick | Aged Red Corner Unit | | | NQLD | 230 | 110 | 76 | DW0 | | 1008 | <17 | 4.0-8.0 | | General Purpose | Slight | Slight | |
| Thin Brick | Castellana Facing Unit | | | NQLD | 230 | 22 | 76 | DW1 | 48.5 | 1920 | <6 | <0.8 | | Exposure Grade | Slight | | 67 |
| Thin Brick | Glazed White Facing Unit | | | NQLD | 230 | 22 | 76 | DW1 | 48.5 | 1920 | <6 | <0.8 | | Exposure Grade | Slight | | 66.4 |
| Thin Brick | Glazed Black Facing Unit | | | NQLD | 230 | 22 | 76 | DW1 | 48.5 | 1920 | <6 | <0.8 | | Exposure Grade | Slight | | 1 |
| Thin Brick | Miro Facing Unit | | | NQLD | 230 | 22 | 76 | DW1 | 48.5 | 1920 | <6 | <0.8 | | Exposure Grade | Slight | | 63.7 |
| Thin Brick | Miro Corner Unit | | | NQLD | 230 | 110 | 76 | DW1 | | 1200 | <6 | <0.8 | | Exposure Grade | Slight | | 63.7 |
| Thin Brick | Azul Corner Unit | | | NQLD | 230 | 110 | 76 | DW1 | | 1200 | <6 | <0.8 | | Exposure Grade | Slight | | 13.1 |
| Thin Brick | Original Corner Unit | | | NQLD | 230 | 110 | 76 | DW0 | | 1008 | <17 | 4.0-8.0 | | General Purpose | Slight | Slight | |
| Thin Brick | Opaque Slate Facing Unit | | | NQLD | 230 | 22 | 76 | DW0 | 48.5 | 2160 | <15 | 4.0-8.0 | <1.0 | General Purpose | Slight | Slight | 24.9 |
| Thin Brick | Romero Corner Unit | | | NQLD | 230 | 110 | 76 | DW1 | | 1200 | <6 | <0.8 | | Exposure Grade | Slight | | 12 |
| Thin Brick | Romero Facing Unit | | | NQLD | 230 | 22 | 76 | DW1 | 48.5 | 1920 | <6 | <0.8 | | Exposure Grade | Slight | | 12 |

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.

| Product Range | Product Name | Dimension Illustration | Swatch | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Units per Square Metre | Pack Size | Maximum Cold Water Absorption (%) | Initial Rate of Absorption (IRA)(kg/m ² min) | Coefficient of Expansion Factor (mm/m) | Durability Class | Liability to Efflorescence | Lime Pitting Liability | LRV |
|---------------|--------------------------|---|---|-------|-------------|------------|-------------|----------------------|------------------------|-----------|-----------------------------------|---|--|------------------|----------------------------|------------------------|------|
| Thin Brick | Glazed Black Corner Unit |  |  | NQLD | 230 | 110 | 76 | DW1 | | 1200 | <6 | <0.8 | | Exposure Grade | Slight | | 1 |
| Thin Brick | Opaque Slate Corner Unit |  |  | NQLD | 230 | 110 | 76 | DW0 | | 1008 | <15 | 4.0-8.0 | <1.0 | General Purpose | Slight | Slight | 24.9 |
| Thin Brick | Aged Red Facing Unit |  |  | NQLD | 230 | 22 | 76 | DW0 | 48.5 | 2160 | <17 | 4.0-8.0 | | General Purpose | Slight | Slight | |

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.