

















Everyday Life Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Everyday Life	Engage			NSW	230	110	76	DW1	2.7	48.5	400	>15	10	0.1-1.0	1.0	Exposure Grade	Slight	Slight	18.3
Everyday Life	Freedom			NSW	230	110	76	DW1	2.7	48.5	400	>15	10	0.1-1.0	1.0	Exposure Grade	Slight	Slight	18.4
Everyday Life	Leisure			NSW	230	110	76	DW1	2.7	48.5	400	>15	10	0.1-1.0	1.0	Exposure Grade	Slight	Slight	14.1
Everyday Life	Escape			NSW	230	110	76	DW1		48.5	400	>15	10	0.1-1.0	1.0	General Purpose	Slight	Slight	8.1
Everyday Life	Stimulate			NSW	230	110	76	DW1	2.7	48.5	400	>15	10	0.1-1.0	1.0	Exposure Grade	Slight	Slight	15
Everyday Life	Unwind			NSW	230	110	76	DW1	2.7			>15	10	0.1-1.0	1.0	Exposure Grade	Slight	Slight	10.5
Everyday Life	Holiday			NSW	230	110	76	DW1	2.7	48.5	400	>15	10	0.1-1.0	1.0		Slight	Slight	10.5
Everyday Life	Retreat			NSW	230	110	76	DW1	2.7	48.5	400	>15	10	0.1-1.0	1.0		Slight	Slight	15.8

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.