









# Metallix Range Technical Data Sheet

# BRICKWORKS

Product Range	Product Name	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f <sub>uc</sub> ) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Metallix	Gunmetal Blue		NSW	230	110	76	DW1		48.5	400	>10	10	0.1-4.0	1.2	Exposure Grade	Nil to slight	Nil to slight	10.8
Metallix	Cuprum		NSW	230	110	76	DW1	3.2	48.5	400	>15	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	13.7
Metallix	Platinum		NSW	230	110	76	DW1	2.8	48.5	400	>15	8	0.1-4.0	1.2	Exposure Grade	Slight	Slight	26.1
Metallix	Blackstone		NSW	230	110	76	DW1		48.5	400	>10	10	0.1-4.0	1.2	Exposure Grade	Nil to slight	Nil to slight	5.9
Metallix	Quartz		NSW	230	110	76	DW1		48.5	400	>10	10	0.1-4.0	1.2	Exposure Grade	Nil to slight	Nil to slight	49.9
Metallix	Titanium		NSW	230	110	76	DW1		48.5	400	>10	10	0.1-3.0	1.2	Exposure Grade	Nil to slight	Nil to slight	12.5
Metallix	Cherry Soda		NSW	230	110	76	DW1		48.5	400	>10	10	0.1-4.0	1.2	Exposure Grade	Nil to slight	Nil to slight	10.3
Metallix	Bronze		NSW	230	110	76	DW1		48.5	400	>10	10	0.5-1.5	1.2	Exposure Grade	Slight	Slight	

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.