

# Park Lane Range Technical Data Sheet

**BRICKWORKS**

| Product Range | Product Name | Dimension Illustration  | Swatch  | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Average Weight / Unit (kg) | Units per Square Metre | Pack Size | Characteristic Unconfined Compressive Strength (f <sub>uc</sub> ) MPa | Maximum Cold Water Absorption (%) | Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min) | Coefficient of Expansion Factor (mm/m) | Durability Class | Liability to Efflorescence | Lime Pitting Liability | LRV  |
|---------------|--------------|---|---|-------|-------------|------------|-------------|----------------------|----------------------------|------------------------|-----------|---|-----------------------------------|--|--|------------------|----------------------------|------------------------|------|
| Park Lane     | Dorchester   |  |  | NSW   | 230         | 110        | 76          | DW1                  |                            | 48.5                   | 400       | >10   | 10                                | 0.1-1.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 | 11.3 |
| Park Lane     | Grosvenor    |  |  | NSW   | 230         | 110        | 76          | DW1                  |                            | 48.5                   | 400       | >10   | 10                                | 0.1-1.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 | 15.7 |
| Park Lane     | Biltmore     |  |  | NSW   | 230         | 110        | 76          | DW1                  | 2.7                        | 48.5                   | 400       | >10   | 10                                | 0.1-1.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 | 12.7 |
| Park Lane     | Chesterfield |  |  | NSW   | 230         | 110        | 76          | DW1                  | 2.7                        | 48.5                   | 400       | >10   | 10                                | 0.1-1.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 | 17.7 |
| Park Lane     | Mayfair      |  |  | NSW   | 230         | 110        | 76          | DW1                  | 2.7                        | 48.5                   | 400       | >10   | 10                                | 0.1-1.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 | 14.2 |
| Park Lane     | Westminster  |  |  | NSW   | 230         | 110        | 76          | DW1                  | 2.7                        | 48.5                   | 400       | >10   | 10                                | 0.1-1.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 | 19   |

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.