











Symmetry Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Symmetry	Portland			NSW	230	110	76	DW1	3	48.5	400	>10	10	0.1-4.0	1.2	General Purpose	Nil to slight	Nil to slight	27.5
Symmetry	Terracotta			NSW	230	110	76	DW1	3	48.5	400	>10	10	0.1-4.0	1.2	Exposure Grade	Nil to slight	Nil to slight	16.6
Symmetry	Asphalt			NSW	230	110	76	DW1		48.5	400	>10	10	0.1-4.0	1.2	Exposure Grade	Nil to slight	Nil to slight	16.2
Symmetry	Earth			NSW	230	110	76	DW1		48.5	400	>10	10	0.1-4.0	1.2	Exposure Grade	Nil to slight	Nil to slight	12.1
Symmetry	Cottage			NSW	230	110	76	DW2	3.1	48.5	400					General Purpose			

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.