




Vogue Collection Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f'uc) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m2 min)	Coefficient of Expansion e'Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability
Vogue Collection	Café Del Mar		NSW	230	110	76	DW1	3	48.5	400	>15	10	0.1 to 2	1.2	General Purpose	Nil to Slight	Nil to Slight
Vogue Collection	Sorano		NSW	230	110	76	DW1	3	48.5	400	>15	10	0.1 to 2	1.2	Exposure Grade	Nil to Slight	Nil to Slight
Vogue Collection	Manhattan		NSW	230	110	76	DW1	2.7	48.5	400	>15	10	0.1 to 2	1.2	Exposure Grade	Slight	Slight
Vogue Collection	Siena		NSW	230	110	76			48.5	512						Nil to Slight	Nil to Slight
Vogue Collection	Crema		NSW	230	110	76	DW1	2.7	48.5	512	>15	10	0.1 to 2	1.2	Exposure Grade	Nil to Slight	Nil to Slight
Vogue Collection	Tuscany		NSW	230	110	76	DW1	3	48.5	400	>15	10	0.1 to 2	1.2	Exposure Grade	Nil to Slight	Nil to Slight
Vogue Collection	Vienna		NSW	230	110	76	DW1	3	48.5	400	>15	10	0.1 to 2	1.2	Exposure Grade	Nil to Slight	Nil to Slight

This Data represents average results from commercial production lots.
If specific test results are required, sample should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

