







La Paloma Grande 50 Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Core Volume (%)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
La Paloma Grande 50	Castellana			NSW	290	110	50	DW1	38	56	459	>15	<10	<1.0	<1.2	Exposure Grade	Slight	Slight	65.3
La Paloma Grande 50	Romero			NSW	290	110	50	DW1	38	56	459	>15	<10	<1.0	<1.2	Exposure Grade	Slight	Slight	20.9
La Paloma Grande 50	Miro			NSW	290	110	50	DW1	38	56	459	>15	<8	<1.0	<1.2	Exposure Grade	Slight	Slight	65.7

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.