

Bowral Remastered Range Technical Data Sheet

BRICKWORKS

| Product Range     | Name      | Dimension Illustration                                                            | Swatch Image                                                                      | State | Length | Width | Height | Dimensional Category | Average Weight / Unit (kg) | Core Volume (%) | Units per sqm | Pack Size | Characteristic Unconfined Compressive Strength | Liability To Effloresce | Lime Pitting Liability | Frl        |
|-------------------|-----------|-----------------------------------------------------------------------------------|-----------------------------------------------------------------------------------|-------|--------|-------|--------|----------------------|----------------------------|-----------------|---------------|-----------|------------------------------------------------|-------------------------|------------------------|------------|
| Bowral Remastered | Oxley     |  |  | NSW   | 230    | 110   | 76     | DW1                  | 3.8                        | Solid           | 48.5          | 384       | >8                                             | Slight                  | Slight                 | 180/180/90 |
| Bowral Remastered | Westow    |  |  | NSW   | 230    | 110   | 76     | DW1                  | 3.8                        | Solid           | 48.5          | 384       | >8                                             | Slight                  | Slight                 | 180/180/90 |
| Bowral Remastered | Moss Vale |  |  | NSW   | 230    | 110   | 76     | DW1                  | 3.8                        | Solid           | 48.5          | 384       | >8                                             | Slight                  | Slight                 | 180/180/90 |
| Bowral Remastered | St Jude   |  |  | NSW   | 230    | 110   | 76     | DW1                  | 3.8                        | Solid           | 48.5          | 384       | >8                                             | Slight                  | Slight                 | 180/180/90 |
| Bowral Remastered | Gibraltar |  |  | NSW   | 230    | 110   | 76     | DW1                  | 3.8                        | Solid           | 48.5          | 384       | >12                                            | Slight                  | Slight                 | 180/180/90 |

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.