Daniel Robertson 470 Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Average Weight / Unit (kg)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability
Daniel Robertson 470	Red			NSW	470	110	50	DW0	4.1	35	288	>10	0.5-2.5	Exposure Grade	Slight	Slight
Daniel Robertson 470	London			NSW	470	110	50	DW0	4.1	35	288	>10	0.5-2.5	Exposure Grade	Slight	Slight
Daniel Robertson 470	Grey Blend			NSW	470	110	50	DW0	4.1	35	288	>10	0.5-2.5	Exposure Grade	Slight	Slight
Daniel Robertson 470	Apricot			NSW	470	110	50	DW0	4.1	35	288	>10	0.5-2.5	Exposure Grade	Slight	Slight
Daniel Robertson 470	Black			NSW	470	110	50	DW0	4.1	35	288	>10	0.5-2.5	Exposure Grade	Slight	Slight

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.