

La Paloma Grande 50 Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Core Volume (%)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Durability Class	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix
La Paloma Grande 50	Castellana			NSW	290	110	50	DW1	38	56	459	>15	Exposure Grade	Slight	Slight	0.23	65.3	Light
La Paloma Grande 50	Romero			NSW	290	110	50	DW1	38	56	459	>15	Exposure Grade	Slight	Slight	0.85	20.9	Light
La Paloma Grande 50	Miro			NSW	290	110	50	DW1	38	56	459	>15	Exposure Grade	Slight	Slight	0.2	65.7	Dark

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.