# La Paloma Grande 50 Range Technical Data Sheet

BRICKWORKS

| Product Range | Name | Dimension Illustration | Swatch Image | State | Length | Width | Height | Dimensional Category | Core Volume (%) | Units per sqm | Pack Size | Characteristic Unconfined Compressive Strength | Durability Class | Liability To Effloresce | Lime Pitting Liability | Solar Absorption | Lrv | Basix |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| La Paloma Grande 50 | Castellana | | | NSW | 290 | 110 | 50 | DW1 | 38 | 56 | 459 | >15 | Exposure Grade | Slight | Slight | 0.23 | 65.3 | Light |
| La Paloma Grande 50 | Romero | | | NSW | 290 | 110 | 50 | DW1 | 38 | 56 | 459 | >15 | Exposure Grade | Slight | Slight | 0.85 | 20.9 | Light |
| La Paloma Grande 50 | Miro | | | NSW | 290 | 110 | 50 | DW1 | 38 | 56 | 459 | >15 | Exposure Grade | Slight | Slight | 0.2 | 65.7 | Dark |

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

austral bricks

Please note: FRL applies up to 3m high - restrained on top and bottom.