Pottery Blend Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Compressive Strength	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix	Frl
Pottery Blend	Charred Clay			NSW	390	110	50	DW2	41.66	348	>10	>10	1.0-3.0	Exposure Grade	Slight	Slight	0.73	12.7	Dark	90/90/90
Pottery Blend	Flamed Earth			NSW	230	110	76	DW2	48.5	520	>10	>10	0.5-2.0	Exposure Grade	Slight	Slight			Dark	90/90/90
Pottery Blend	Clay Blush			NSW	230	110	76	DW2	48.5	520	>10	>10	0.5-2.0	Exposure Grade	Slight	Slight			Dark	90/90/90
Pottery Blend	Fired Umber			NSW	230	110	76	DW2	48.5	520	>10	>10	0.5-2.0	Exposure Grade	Slight	Slight			Dark	90/90/90
Pottery Blend	Raku Rouge			NSW	390	110	50	DW2	41.66	348	>10	>10	1.0-3.0	Exposure Grade	Slight	Slight	0.76	11.5	Dark	90/90/90
Pottery Blend	Burnished Tan			NSW	390	110	50	DW2	41.66	348	>10	>10	1.0-3.0	Exposure Grade	Slight	Slight	0.77	10.6	Dark	90/90/90
Pottery Blend	Bisque Fire			NSW	390	110	50	DW2	41.66	348	>10	>10	1.0-3.0	Exposure Grade	Slight	Slight	0.67	15.6	Dark	90/90/90

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

australbricks

Please note: FRL applies up to 3m high - restrained on top and bottom.