San Selmo Classico Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Swatch Image	State	Length	Width	Height	Dimensional Category	Core Volume (%)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Efactor	Durability Class	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix
San Selmo Classico	Aged Red		NSW	230	110	76	DW0	Solid	48.5	336	>8	0.8	General Purpose	Slight	Slight	0.69	22.8	medium
San Selmo Classico	Original		NSW	230	110	76	DWD		48.5	336	>8	0.8	General Purpose	Slight	Slight	0.46	35.5	Medium
San Selmo Classico	Limewash		NSW	230	110	76	DW0	Solid	48.5	336	>8	0.8	General Purpose	Slight	Slight	0.54	53.2	light

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.

austral bricks