Whitsunday AB Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Average Weight / Unit (kg)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Durability Class	Liability To Effloresce	Lime Pitting Liability	Basix	Frl
Whitsunday AB	Orpheus			NSW	230	110	76	DW1	2.7	48.5	520	>10	Exposure Grade	Slight	Slight	Dark	90/90/90
Whitsunday AB	Brampton			NSW	230	110	76	DW1		48.5	520	>10	Exposure Grade	Slight	Slight	Medium	90/90/90

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

austral bricks

Please note: FRL applies up to 3m high - restrained on top and bottom.