Bowral 50 Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Average Weight / Unit (kg)	Core Volume (%)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix	Frl
Bowral 50	Bowral Blue			NSW	230	110	50	DW1	2.5	Solid	69.5	570	>12	1 to 8	Exposure Grade	Nil to slight	Nil to slight	0.838	7.78	Dark	180/180/90
Bowral 50	Capitol Red			NSW	230	110	50	DW1	3.8	Solid	69.5	570	>12	1 to 8	Exposure Grade	Nil to slight	Nil to slight	0.7268	16.78	Dark	180/180/90
Bowral 50	Simmental Silver			NSW	230	110	50	DW1	2.5	Solid	69.5	570	>8	1 to 8	Exposure Grade	Nil to slight	Nil to slight	0.584	33.33	Medium	180/180/90
Bowral 50	Hereford Bronze			NSW	230	110	50	DW1	2.5	Solid	69.5	570	>12	1 to 8	Exposure Grade	Nil to slight	Nil to slight	0.7553	17.33	Dark	180/180/90
Bowral 50	St Pauls Cream			NSW	230	110	50	DW1	3.8	Solid	69.5	570	>8	1.0-4.0	Exposure Grade	Slight	Slight	0.51	41		
Bowral 50	Brahman Granite			NSW	230	110	50	DW1	2.5	Solid	69.5	570	>12	1 to 8	Exposure Grade	Nil to slight	Nil to slight	0.7915	10	Dark	180/180/90
Bowral 50	Renovation Gertrudis Brown			NSW	230	110	50	DW1	2.5	Solid	69.5	570	>12	1 to 8	Exposure Grade	Nil to slight	Nil to slight				180/180/90
Bowral 50	Chillingham White			NSW	230	110	50	DW1	2.5	Solid	69.5	570	>8	1 to 8	Exposure Grade	Nil to slight	Nil to slight	0.343	66.44	Light	180/180/90
Bowral 50	Gertrudis Brown			NSW	230	110	50	DW1	2.5	Solid	69.5	570	>12	1 to 8	Exposure Grade	Nil to slight	Nil to slight	0.805	11.4	Dark	180/180/90
Bowral 50	Bowral Brown			NSW	230	110	50	DW1	2.5	Solid	69.5	570	>12	1 to 8	Exposure Grade	Nil to slight	Nil to slight	0.808	14.11	Dark	180/180/90
Bowral 50	Embassy Red			NSW	230	110	50	DW1		Solid	69.5	570	>8	4.0-6.0	Exposure Grade	Slight	Slight	0.73	11.1		
Bowral 50	Murray Grey			NSW	230	110	50	DW1	2.5	Solid	69.5	570	>12	1 to 8	Exposure Grade	Nil to slight	Nil to slight	0.684	18	Medium	180/180/90

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

BOWRAL BRICKS

Please note: FRL applies up to 3m high - restrained on top and bottom.