

Bowral Highlands Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Average Weight / Unit (kg)	Core Volume (%)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Compressive Strength	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix	Frl
Bowral Highlands	Sutton			NSW	230	110	76	DW1		Solid	48.5	384	>8		4.0-6.0	Exposure Grade	Slight	Slight				
Bowral Highlands	Burrawang			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8		1 to 8	Exposure Grade	Slight	Slight				180/180/90
Bowral Highlands	Wingello			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8		1 to 8	Exposure Grade	Slight	Slight	0.37	28.33	Light	180/180/90
Bowral Highlands	Welby			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8		1 to 8	Exposure Grade	Slight	Slight				180/180/90
Bowral Highlands	Meryla			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8		1 to 8	Exposure Grade	Slight	Slight	0.4	27.8	Light	180/180/90
Bowral Highlands	Penrose			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8		1 to 8	Exposure Grade	Slight	Slight				180/180/90
Bowral Highlands	Bangadilly			NSW	230	110	76	DW1	3.8	Solid	48.5		>8	>12			Slight	Slight			Medium	180/180/90

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.