

Commons Range Technical Data Sheet

BRICKWORKS

| Product Range | Name                  | Dimension Illustration                                                            | Swatch Image                                                                      | State | Length | Width | Height | Dimensional Category | Average Weight / Unit (kg) | Core Volume (%) | Units per sqm | Pack Size | Characteristic Unconfined Compressive Strength | Compressive Strength | Initial Rate Of Absorption | Durability Class | Liability To Effloresce | Lime Pitting Liability | Frl         |
|---------------|-----------------------|-----------------------------------------------------------------------------------|-----------------------------------------------------------------------------------|-------|--------|-------|--------|----------------------|----------------------------|-----------------|---------------|-----------|------------------------------------------------|----------------------|----------------------------|------------------|-------------------------|------------------------|-------------|
| Commons       | Maxi 76               |  |  | NSW   | 230    | 90    | 76     | DW1                  |                            |                 | 48.5          | 400       | >15                                            |                      |                            |                  | Nil to slight           | Nil to slight          | 240/240/120 |
| Commons       | Standard 119          |  |  | NSW   | 230    | 110   | 119    | DW1                  |                            |                 | 32.3          |           | >15                                            | >25                  |                            |                  | Nil to slight           | Nil to slight          | 240/240/120 |
| Commons       | Universal Exposure 76 |  |  | NSW   | 230    | 110   | 76     | DW1                  | 2.6                        |                 | 48.5          | 400       | >15                                            |                      | 0.5 to 3                   | Exposure Grade   | Nil to slight           | Nil to slight          | 240/240/120 |
| Commons       | GP 76                 |  |  | NSW   | 230    | 110   | 76     | DW2                  |                            |                 | 24.25         | 520       |                                                |                      | 1.0-3.0                    | General Purpose  |                         |                        |             |
| Commons       | Dry Press             |  |  | NSW   | 230    | 110   | 76     | DW1                  |                            | Solid           | 48.5          |           | >15                                            | >12                  |                            |                  | Slight                  |                        | 180/180/90  |
| Commons       | Avanti                |  |  | NSW   | 230    | 110   | 162    |                      |                            |                 | 24.25         | 260       |                                                | >15                  | 1.0-4.0                    | Exposure Grade   |                         | Slight                 |             |
| Commons       | Unicommons            |  |  | NSW   | 230    | 110   | 76     | DW2                  |                            |                 | 48.5          | 520       | >10                                            |                      | 1.0-3.0                    | General Purpose  |                         | Slight                 |             |
| Commons       | Universal 76          |  |  | NSW   | 230    | 110   | 76     | DW1                  | 2.6                        |                 | 48.5          | 400       | >15                                            |                      | 0.5 to 3                   | General Purpose  | Nil to slight           | Nil to slight          | 240/240/120 |
| Commons       | Exposure 76           |  |  | NSW   | 230    | 110   | 76     | DW1                  |                            |                 | 48.6          | 400       | >15                                            |                      | 0.5 to 3                   | Exposure Grade   | Nil to slight           | Nil to slight          | 240/240/120 |
| Commons       | Standard 162          |  |  | NSW   | 230    | 110   | 162    | DW1                  | 6                          |                 | 24.25         |           | >25                                            | >20                  |                            |                  | Nil to slight           | Nil to slight          | 240/240/120 |
| Commons       | Standard 76           |  |  | NSW   | 230    | 110   | 76     | DW1                  | 2.6                        |                 | 48.5          | 400       | >15                                            |                      | 0.5 to 3                   | General Purpose  | Slight                  |                        | 240/240/120 |

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.