Commons Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Average Weight / Unit (kg)	Core Volume (%)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Compressive Strength	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability	Frl
Commons	Maxi 76			NSW	230	90	76	DW1			48.5	400	>15				Nil to slight	Nil to slight	240/240/120
Commons	Standard 119			NSW	230	110	119	DW1			32.3		>15	>25			Nil to slight	Nil to slight	240/240/120
Commons	Universal Exposure 76			NSW	230	110	76	DW1	2.6		48.5	400	>15		0.5 to 3	Exposure Grade	Nil to slight	Nil to slight	240/240/120
Commons	Dry Press			NSW	230	110	76	DW1		Solid	48.5		>15	>12			Slight		180/180/90
Commons	Universal 76			NSW	230	110	76	DW1	2.6		48.5	400	>15		0.5 to 3	General Purpose	Nil to slight	Nil to slight	240/240/120
Commons	Exposure 76			NSW	230	110	76	DW1			48.6	400	>15		0.5 to 3	Exposure Grade	Nil to slight	Nil to slight	240/240/120
Commons	Standard 162			NSW	230	110	162	DW1	6		24.25		>25	>20			Nil to slight	Nil to slight	240/240/120
Commons	Standard 76			NSW	230	110	76	DW1	2.6		48.5	400	>15		0.5 to 3	General Purpose	Slight		240/240/120

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

austral bricks

Please note: FRL applies up to 3m high - restrained on top and bottom.