



La Paloma Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Average Weight / Unit (kg)	Core Volume (%)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix
La Paloma	Castellana			NSW	230	110	76	DW1		38	48.5	432	>15		Exposure Grade	Slight	Slight	0.23	65.3	Light
La Paloma	Palma			NSW	290	70	50	DW1	1.38		56	714	>15	0.1-0.8		Slight	Slight	0.23	63.7	
La Paloma	Tenerife			NSW	290	70	76	DW1	2.3		38.8	462	>15			Nil to Slight	Nil to Slight		4.5	
La Paloma	Seville			NSW	290	70	76	DW1	2.3		38.8	462	>15			Nil to Slight	Nil to Slight		64.1	
La Paloma	Madrid			NSW	290	70	76	DW1	2.3		38.8	462	>15			Nil to Slight	Nil to Slight		65.8	
La Paloma	Elda			NSW	230	70	76	DW1	1.7		48.5	624	>15	0.1-0.8		Slight	Slight	0.85	4.5	
La Paloma	Lorca			NSW	230	70	76	DW1	1.7		48.5	624	>15	0.1-0.8		Slight	Slight	0.23	63.7	
La Paloma	Lanzarote			NSW	230	70	119	DW1	2.7		32.3	416	>15			Nil to Slight	Nil to Slight		4.5	
La Paloma	Romero			NSW	230	110	76	DW1		38	48.5	432	>15		Exposure Grade	Slight	Slight	0.85	20.9	Dark
La Paloma	Terrassa			NSW	230	70	119	DW1	2.7		32.3	416	>15			Nil to Slight	Nil to Slight		67	
La Paloma	Azul			NSW	230	110	76	DW1	2.3	38	48.5	432	>15		Exposure Grade	Slight	Slight	0.86	13.3	Dark
La Paloma	Toledo			NSW	290	70	50	DW1	1.38		56	714	>15	0.1-0.8		Slight	Slight	0.23	4.5	
La Paloma	Azul			NSW	230	80	76	DW1	2.3		48.5	462	>15			Nil to Slight	Nil to Slight		13.5	
La Paloma	Alicante			NSW	230	70	119	DW1	2.7		32.3	416	>15			Nil to Slight	Nil to Slight		65.8	
La Paloma	Pamplona			NSW	290	70	76	DW1	2.3		38.8	462	>15			Nil to Slight	Nil to Slight		28.1	
La Paloma	Miro			NSW	230	110	76	DW1		38	48.5	432	>15		Exposure Grade	Slight	Slight	0.2	65.7	Light

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.