# San Selmo Corso Range Technical Data Sheet

BRICKWORKS

| Product Range | Name | Dimension Illustration | Swatch Image | State | Length | Width | Height | Dimensional Category | Core Volume (%) | Units per sqm | Pack Size | Characteristic Unconfined Compressive Strength | Initial Rate Of Absorption | Durability Class | Liability To Effloresce | Lime Pitting Liability | Solar Absorption | Lrv | Basix |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| San Selmo Corso | Piave | | | NSW | 500 | 100 | 40 | DW0 | Solid | 40.8 | | >10 | 1.0-8.0 | General Purpose | Nil to slight | Nil to slight | | | Dark |
| San Selmo Corso | Potenza | | | NSW | 500 | 100 | 40 | DW0 | Solid | 40.8 | 137 | >10 | 1.0-8.0 | General Purpose | Nil to slight | Nil to slight | 0.73 | 9.2 | Dark |
| San Selmo Corso | Marana | | | NSW | 500 | 100 | 40 | DW0 | Solid | 40.8 | | >10 | 1.0-8.0 | General Purpose | Nil to slight | Nil to slight | 0.77 | 14.8 | Dark |
| San Selmo Corso | Potenza | | | NSW | 500 | 100 | 40 | DW0 | Solid | 40.8 | | >10 | 1.0-8.0 | General Purpose | Nil to slight | Nil to slight | 0.73 | 9.2 | Medium |
| San Selmo Corso | Marana | | | NSW | 500 | 100 | 40 | DW0 | Solid | 40.8 | 137 | >10 | 1.0-8.0 | General Purpose | Nil to slight | Nil to slight | 0.77 | 14.8 | Dark |
| San Selmo Corso | Livenza | | | NSW | 500 | 100 | 40 | DW0 | Solid | 40.8 | | >10 | 1.0-8.0 | General Purpose | Nil to slight | Nil to slight | 0.72 | 20.1 | Light |
| San Selmo Corso | Brenta | | | NSW | 500 | 100 | 40 | DW0 | Solid | 40.8 | 137 | >10 | 1.0-8.0 | General Purpose | Nil to slight | Nil to slight | 0.35 | 48.5 | Dark |
| San Selmo Corso | Arno | | | NSW | 500 | 100 | 40 | DW0 | Solid | 40.8 | | >10 | 1.0-8.0 | General Purpose | Nil to slight | Nil to slight | 0.66 | 19 | Light |
| San Selmo Corso | Livenza | | | NSW | 500 | 100 | 40 | DW0 | Solid | 40.8 | 137 | >10 | 1.0-8.0 | General Purpose | Nil to slight | Nil to slight | 0.72 | 20.1 | Dark |
| San Selmo Corso | Brenta | | | NSW | 500 | 100 | 40 | DW0 | Solid | 40.8 | | >10 | 1.0-8.0 | General Purpose | Nil to slight | Nil to slight | 0.35 | 48.5 | Light |
| San Selmo Corso | Piave | | | NSW | 500 | 100 | 40 | DW0 | Solid | 40.8 | 137 | >10 | 1.0-8.0 | General Purpose | Nil to slight | Nil to slight | | | Dark |
| San Selmo Corso | Arno | | | NSW | 500 | 100 | 40 | DW0 | Solid | 40.8 | 137 | >10 | 1.0-8.0 | General Purpose | Nil to slight | Nil to slight | 0.66 | 19 | Dark |

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

austral bricks

Please note: FRL applies up to 3m high - restrained on top and bottom.