Urban One Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix	Frl
Urban One	Silver NSW			NSW	230	110	76	DW1	48.5	400	>10	0.5 to 3	Exposure Grade	Slight	Slight	0.579	31.2	Medium	90/90/90
Urban One	Pepper NSW			NSW	230	110	76	DW1	48.5	520	>10	0.5 to 3	Exposure Grade	Slight	Slight	0.755	13.67	Dark	90/90/90
Urban One	Chiffon NSW			NSW	230	110	76	DW1	48.5	400	>10	0.5 to 3.0	Exposure Grade	Slight	Slight	0.7388	15.25	Dark	90/90/90

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

austral bricks

Please note: FRL applies up to 3m high - restrained on top and bottom.