

La Paloma 50 Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f'uc) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m2 min)	Coefficient of Expansion e Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
La Paloma 50	Azul			SA	230	110	50	DW1	1.8	69.5	648	15	10	1.0	1.2	Exposure Grade	Slight	Slight	13.3
La Paloma 50	Castellana			SA	230	110	50	DW1	1.8	69.5	648	15	10	1.0	1.2	Exposure Grade	Slight	Slight	65.3
La Paloma 50	Miro			SA	230	110	50	DW1	1.8	69.5	648	15	10	1.0	1.2	Exposure Grade	Slight	Slight	65.7
La Paloma 50	Romero			SA	230	110	50	DW1	1.8	69.5	648	15	10	1.0	1.2	Exposure Grade	Slight	Slight	20.9

This Data represents average results from commercial production lots.
If specific test results are required, sample should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.