





Archetype Warm Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability
Archetype Warm	Mellow		SA	230	110	76	DW1	2.5	48.5	400	>10	10	0.5-1.5	1.2	General Purpose	Slight	Slight
Archetype Warm	Optic		SA	230	110	76	DW1	2.5	48.5	400	>10	10	0.5-1.5	1.2	General Purpose	Slight	Slight
Archetype Warm	Jute		SA	230	110	76	DW1	2.5	48.5	400	>10	10	0.5-1.5	1.2	General Purpose	Slight	Slight
Archetype Warm	Glacier		SA	230	110	76	DW1	2.5	48.5	400	>10	10	0.5-1.5	1.2	General Purpose	Slight	Slight

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.