

Palm Springs Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Palm Springs	Mirage		SQLD	230	110	76	DW2	2.3	48.5	520	>15	9	0.5-2.0	1.0	Exposure Grade	Slight	Slight	22.2
Palm Springs	Mirador		SQLD	230	110	76	DW2	2.3	48.5	520	>15	9	0.5-2.0	1.0	Exposure Grade	Slight	Slight	20.4
Palm Springs	Oasis		SQLD	230	110	76	DW2	2.3	48.5	520	>15	9	0.5-2.0	1.0	Exposure Grade	Slight	Slight	44.7
Palm Springs	Desert		SQLD	230	110	76	DW2	2.3	48.5	520	>15	9	0.5-2.0	1.0	Exposure Grade	Slight	Slight	26.4
Palm Springs	Newport		SQLD	230	110	76	DW2	2.3	48.5	520	>15	9	0.5-2.0	1.0	Exposure Grade	Slight	Slight	13.2

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.