

















Pottery Blend Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Pottery Blend	Bisque Fire			SQDL	390	110	50	DW2	2.9	41.66	348	>13	8	1.0-3.0	1.0	Exposure Grade	Slight	Slight	15.6
Pottery Blend	Burnished Tan			SQDL	390	110	50	DW2		41.66	348	>13	8	1.0-3.0	1.0	Exposure Grade	Slight	Slight	10.6
Pottery Blend	Charred Clay			SQDL	390	110	50	DW2		41.66	348	>13	8	1.0-3.0	1.0	Exposure Grade	Slight	Slight	12.7
Pottery Blend	Raku Rouge			SQDL	390	110	50	DW2		41.66	348	>13	8	1.0-3.0	1.0	Exposure Grade	Slight	Slight	11.5
Pottery Blend	Warm Tan			SQDL	230	110	76	DW2	2.4	48.5	520	>15	8	0.5-2.0	1.0	Exposure Grade	Slight	Slight	16.7
Pottery Blend	Flamed Earth			SQDL	230	110	76	DW2	2.4	48.5	520	>15	8	0.5-2.0	1.0	Exposure Grade	Slight	Slight	
Pottery Blend	Clay Blush			SQDL	230	110	76	DW2	2.4	48.5	520	>15	8	0.5-2.0	1.0	Exposure Grade	Slight	Slight	
Pottery Blend	Fired Umber			SQDL	230	110	76	DW2	2.4	48.5	520	>15	8	0.5-2.0	1.0	Exposure Grade	Slight	Slight	

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.