


Metallix Range Technical Data Sheet



Product Range	Product Name	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f'uc) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m2 min)	Coefficient of Expansion e Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Metallix	Graphite		TAS	230	110	76	DW2	3.2	48.5	400	>15	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	6.6
Metallix	Graphite		TAS	230	110	76	DW2		48.5	384	>15	10	0.5-1.5	1.0	General Purpose	Slight	Slight	
Metallix	Graphite Flash		TAS	230	110	76	DW2		48.5	384	>15	10	0.5-1.5	1.0	General Purpose	Slight	Slight	

This Data represents average results from commercial production lots.
If specific test results are required, sample should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

