

















Nelissen Range Technical Data Sheet

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion e Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability
Nelissen	Charleroi			TAS	230	110	76	DW1	59	730	>5	15	1.0-8.0	1.0	General Purpose	Nil to slight	Nil to slight
Nelissen	Bruges			TAS	230	110	76	DW1	59	730	>5	15	1.0-8.0	1.0	General Purpose	Nil to slight	Nil to slight
Nelissen	Mechelen			TAS	230	110	76	DW1	59	730	>5	15	1.0-8.0	1.0	Exposure Grade	Nil to slight	Nil to slight
Nelissen	Ypres			TAS	230	110	76	DW1	59	730	>5	15	1.0-8.0	1.0	General Purpose	Nil to slight	Nil to slight
Nelissen	Hasselt			TAS	230	110	76	DW1	59	730	>5	15	1.0-8.0	1.0	General Purpose	Nil to slight	Nil to slight
Nelissen	Tournai			TAS	230	110	76	DW1	59	730	>5	15	1.0-8.0	1.0	General Purpose	Nil to slight	Nil to slight
Nelissen	Ostend			TAS	230	110	76	DW1	59	730	>5	15	1.0-8.0	1.0	General Purpose	Nil to slight	Nil to slight
Nelissen	Limburg			TAS	230	110	76	DW1	59	730	>5	15	1.0-8.0	1.0	General Purpose	Nil to slight	Nil to slight

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.