

Panorama 50 Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability
Panorama 50	Lunar Crust			TAS	390	110	50	DW2	41.66	348	>13	8	1.0-3.0	1.0	Exposure Grade	Slight	Nil
Panorama 50	Midnight			TAS	390	110	50	DW2	41.66	348	>13	8	1.0-3.0	1.0	Exposure Grade	Slight	Nil
Panorama 50	Night Sky			TAS	390	110	50	DW2	41.66	348	>13	8	1.0-3.0	1.0	Exposure Grade	Slight	Nil
Panorama 50	Snowfield			TAS	390	110	50	DW2	41.66	348	>13	10	1.0-3.0	1.0	General Purpose	Slight	Nil

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.