

















# Pottery Blend Range Technical Data Sheet

**BRICKWORKS**

| Product Range | Product Name  | Dimension Illustration  | Swatch  | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Average Weight / Unit (kg) | Units per Square Metre | Pack Size | Characteristic Unconfined Compressive Strength (f <sub>uc</sub> ) MPa | Maximum Cold Water Absorption (%) | Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min) | Coefficient of Expansion Factor (mm/m) | Durability Class | Liability to Efflorescence | Lime Pitting Liability | LRV  |
|---------------|---------------|---|---|-------|-------------|------------|-------------|----------------------|----------------------------|------------------------|-----------|---|-----------------------------------|--|--|------------------|----------------------------|------------------------|------|
| Pottery Blend | Bisque Fire   |  |  | TAS   | 390         | 110        | 50          | DW2                  | 2.9                        | 41.66                  | 348       | >13   | 8                                 | 1.0-3.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 | 15.6 |
| Pottery Blend | Burnished Tan |  |  | TAS   | 390         | 110        | 50          | DW2                  |                            | 41.66                  | 348       | >13   | 8                                 | 1.0-3.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 | 10.6 |
| Pottery Blend | Charred Clay  |  |  | TAS   | 390         | 110        | 50          | DW2                  |                            | 41.66                  | 348       | >13   | 8                                 | 1.0-3.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 | 12.7 |
| Pottery Blend | Raku Rouge    |  |  | TAS   | 390         | 110        | 50          | DW2                  |                            | 41.66                  | 348       | >13   | 8                                 | 1.0-3.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 | 11.5 |
| Pottery Blend | Warm Tan      |  |  | TAS   | 230         | 110        | 76          | DW2                  | 2.4                        | 48.5                   | 520       | >15   | 8                                 | 0.5-2.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 | 16.7 |
| Pottery Blend | Flamed Earth  |  |  | TAS   | 230         | 110        | 76          | DW2                  | 2.4                        | 48.5                   | 520       | >15   | 8                                 | 0.5-2.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 |      |
| Pottery Blend | Clay Blush    |  |  | TAS   | 230         | 110        | 76          | DW2                  | 2.4                        | 48.5                   | 520       | >15   | 8                                 | 0.5-2.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 |      |
| Pottery Blend | Fired umber   |  |  | TAS   | 230         | 110        | 76          | DW2                  | 2.4                        | 48.5                   | 520       | >15   | 8                                 | 0.5-2.0  | 1.0                                    | Exposure Grade   | Slight                     | Slight                 |      |

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.