









# Coach House Range Technical Data Sheet

**BRICKWORKS**

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Core Volume (%)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f <sub>uc</sub> ) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Coach House	Cream			TAS	230	110	76	DW1	2.8	<30	48.5	384	>7	<12	0.5-2.5	<1.0	General Purpose	Slight	Slight	27.4
Coach House	Tan			TAS	230	110	76	DW2	2.85	<30	48.5	384	>12	<12	0.5-2.5	<1.0	Exposure Grade	Slight	Slight	10.2
Coach House	Red			TAS	230	110	76	DW2	2.85	<30	48.5	384	>12	<10	0.5-2.5	<1.0	Exposure Grade	Slight	Slight	13.8
Coach House	Centennial Blend			TAS	230	110	76	DW1	2.8	<30	48.5	384	>8	<12	0.2-2.5	<1.0	General Purpose	Slight	Slight	27.1

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.