

Domain Range Technical Data Sheet

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Domain	Retreat			VIC	230	110	76	DW2	3.1	48.5	400	>15	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	9.5
Domain	Sanctuary			VIC	230	110	76	DW2	3.1	48.5	400	>15	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	15.2
Domain	Haven			VIC	230	110	76	DW2	3.1	48.5	400	>15	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	10.7
Domain	Oasis			VIC	230	110	76	DW2	3.1	48.5	400	>15	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	29.6
Domain	Anchorage			VIC	230	110	76	DW2	3.1	48.5	400	>15	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	10.1

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.