

Melbourne Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f'uc) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m2 min)	Coefficient of Expansion e Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Melbourne	Black Rock			VIC	230	110	76	DW2	3.2	48.5	400	>15	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	5.7
Melbourne	Canterbury			VIC	230	110	76	DW2	3.2	48.5	400	>15	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	10
Melbourne	Hawthorn			VIC	230	110	76	DW2	3.2	48.5	400	>15	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	7.4
Melbourne	Mornington			VIC	230	110	76	DW2	3.2	48.5	400	>15	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	16.3
Melbourne	Yering			VIC	230	110	76	DW2	3.2	48.5	400	>15	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	10
Melbourne	Strathmore			VIC	230	110	76	DW2		48.5	400	>25	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	
Melbourne	Elwood			VIC	230	110	76	DW2		48.5	400	>25	8	0.2-1.5	1.0	Exposure Grade	Slight	Slight	

This Data represents average results from commercial production lots.
If specific test results are required, sample should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.