

**Range: Utility Bricks and Accessories**

**Colour: 2 Hour Fire Rated Common**

**SKU: utility\_bricks\_and\_accessories\_2\_hour\_fire\_rated\_common**

### Technical Data

Length (mm)	230	Maximum Cold Water Absorption (%)	<12
Width (mm)	110	Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	<2.2
Height (mm)	76	Coefficient of Expansion e'Factor (mm/m)	<0.9
Dimensional Category	DW1	Durability Class	Exposure Grade
Average Weight / Unit (kg)	3.5	Liability to Efflorescence	Slight
Units per Square Metre	48.5	Lime Pitting Liability	Slight
Pack Size	264	Place of Manufacture	Western Australia
Characteristic Unconfined Compressive Strength (f 'uc) MPa	>12	Product Warranty	100 Years

A BRAND OF

**BRICKWORKS**