

















Specialty Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion e Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	FRL
Specialty	Espresso			WA	230	110	76	DW1	2.8	48.5	512	>15	10	0.1 to 2	1.2	Exposure Grade	Nil to slight	Nil to slight	90/90/90
Specialty	Sienna			WA	230	110	76	DW1	2.8	48.5	512	>15	10	0.1 to 2	1.2	Exposure Grade	Nil to slight	Nil to slight	90/90/90
Specialty	Royal			WA	230	110	76	DW1	2.8	48.5	512	>15	10	0.1 to 2	1.2	Exposure Grade	Nil to slight	Nil to slight	90/90/90
Specialty	Crimson			WA	230	110	76	DW1	2.8	48.5	512	>15	10	0.1 to 2	1.2	Exposure Grade	Nil to slight	Nil to slight	90/90/90
Specialty	Pacific			WA	230	110	76	DW1	2.8	48.5	512	>15	10	0.1 to 2	1.2	Exposure Grade	Nil to slight	Nil to slight	90/90/90
Specialty	Emerald			WA	230	110	76	DW1	2.8	48.5	512	>15	10	0.1 to 2	1.2	Exposure Grade	Nil to slight	Nil to slight	90/90/90
Specialty	Jade			WA	230	110	76	DW1	2.8	48.5	512	>15	10	0.1 to 2	1.2	Exposure Grade	Nil to slight	Nil to slight	90/90/90
Specialty	Amber			WA	230	110	76	DW1	2.8	48.5	512	>15	10	0.1 to 2	1.2	Exposure Grade	Nil to slight	Nil to slight	90/90/90

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.