









San Selmo Smoked Range Technical Data Sheet

BRICKWORKS

| Product Range | Product Name | Dimension Illustration | Swatch | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Average Weight / Unit (kg) | Units per Square Metre | Pack Size | Characteristic Unconfined Compressive Strength (f'uc) MPa | Maximum Cold Water Absorption (%) | Initial Rate of Absorption (IRA) (kg/m2 min) | Coefficient of Expansion e Factor (mm/m) | Durability Class | Liability to Efflorescence | Lime Pitting Liability | LRV |
|------------------|---------------|---|---|-------|-------------|------------|-------------|----------------------|----------------------------|------------------------|-----------|---|-----------------------------------|--|--|------------------|----------------------------|------------------------|------|
| San Selmo Smoked | Cloudy Silver |  |  | WA | 230 | 110 | 76 | DW0 | 3.1 | 48.5 | 216 | >10 | 15 | 3.0 | 1.0 | General Purpose | Slight | Slight | 22.8 |
| San Selmo Smoked | Grey Cashmere |  |  | WA | 230 | 110 | 76 | DW0 | 3.1 | 48.5 | 216 | >10 | 15 | 3.0 | 1.0 | General Purpose | Slight | Slight | 46.3 |
| San Selmo Smoked | Opaque Slate |  |  | WA | 230 | 110 | 76 | DW0 | 3.1 | 48.5 | 216 | >10 | 15 | 3.0 | 1.0 | General Purpose | Slight | Slight | 25.3 |
| San Selmo Smoked | Wild Storm |  |  | WA | 230 | 110 | 76 | DW0 | 3.1 | 48.5 | 216 | >10 | 15 | 3.0 | 1.0 | General Purpose | Slight | Slight | 14.1 |

This Data represents average results from commercial production lots.
If specific test results are required, sample should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.